

WHAT IS CLAIMED IS:

1. A continuous process for the preparation of a thermoplastic polyurethane elastomer at a temperature of 130 to 250°C comprising reacting:
- 5 A) at least one polyether diol having a number average molecular weight (M_n) of 450 to 10,000 and, on average, 1.8 to 2.2 Zerewitinoff active hydrogen atoms; with
- B) at least one organic diisocyanate; and
- C) 1,4-di-(2,2'-hydroxyethyl)-hydroquinone,
- 10 in the presence of 10 to 1000 ppm in relation to A) of tin dioctoate as a catalyst
- with the proviso that the NCO/OH ratio of the reactants A), B) and C) is 0.85 to 1.2, said thermoplastic polyurethane having a glass transition temperature (T_g) below 50°C.
- 15 2. The process of Claim 1 wherein the preparation takes place in an extruder.
3. The process of Claim 1 wherein the preparation is carried out
- 20 in a prepolymer process.
4. The process of Claim 2 wherein the preparation is carried out in a prepolymer process.
- 25 5. The polyurethane elastomer prepared in accordance with the process of Claim 1.
6. The polyurethane elastomer of Claim 5 further containing at least one member selected from the group consisting of auxiliary
- 30 substances and accessory agents.